

Fabrication of 3-dimensional Cross-linked redox protein/Nanomaterials

A.K.M. Kafi, * S.N. Nina and Mashitah M. Yusoff

Faculty of Industrial Sciences & Technology, Universiti Malaysia Pahang,
Kuantan 26300, Malaysia

In this work, we have described a new 3-dimensional (3D) network of crosslinked Horseradish Peroxidase/Carbon Nanotube (HRP/CNT) on a thiol-modified Au surface in order to build up the effective electrical wiring of the enzyme units with the electrode. This was achieved by the electropolymerization of aniline-functionalized carbon nanotubes (CNTs) and 4-aminothiophenol -modified-HRP on a 4-aminothiophenol monolayer-modified Au electrode. The synthesized 3D HRP/CNT networks were characterized with cyclic voltammetry and amperometry, resulting the establishment direct electron transfer between the redox active unit of HRP and the Au surface. Electrochemical measurements reveal that the immobilized HRP exhibits high biological activity and stability and a quasi-reversible redox peak of the redox center of HRP was observed at about -0.355 and -0.275 V vs. Ag/AgCl. The electron transfer rate constant, k_s and electron transfer co-efficient α were found to be 0.57 s⁻¹ and 0.42 , respectively. Based on the electrocatalytic process by direct electrochemistry of HRP, a biosensor for detecting H₂O₂ was developed. The developed biosensor exhibits excellent electrocatalytic activity for the reduction of H₂O₂. The proposed biosensor modified with HRP/CNT 3D network displays a broader linear range and a lower detection limit for H₂O₂ determination. The linear range is from 1.0×10^{-7} to 1.2×10^{-4} M with a detection limit of $2.2.0 \times 10^{-8}$ M at 3σ . Moreover, this biosensor exhibits very high sensitivity, good reproducibility and long-time stability. In summary, ease of fabrication, a low cost, fast response and high sensitivity are the main advantages of the new biosensor proposed in this study. These obvious advantages would really help for the real analytical applicability of the proposed biosensor.

* Correspondence to : kafiakm@ump.edu.my