

Dependence of magnetic and microwave loss on evolving microstructure in yttrium iron garnet

Rodziah Nazlan¹ · Ismayadi Ismail² · Raba'ah Syahidah Azis³ · Zulkifly Abbas³ · Idza Riati Ibrahim² · Fadzidah Mohd Idris^{2,4} · Farah Nabilah Shafiee² · Azdiya Suhada Aripin² · Nurul Ainaa Najihah Busra¹

Received: 11 January 2018 / Accepted: 9 March 2018 / Published online: 14 March 2018
© Springer Science+Business Media, LLC, part of Springer Nature 2018

Abstract

The parallel magnetic and microwave loss dependence on microstructural evolutions in several polycrystalline yttrium iron garnet samples were studied in detail, focusing on the attendant occurrence of their relationships. In this study, polycrystalline YIG samples were synthesized by employing the mechanical alloying technique and sintering toroidal compacts at temperatures from 600 to 1400 °C. The samples were characterized for their evolution in crystalline phases, structure, microstructure, magnetic hysteresis parameters, microwave losses and electrical resistivity. The results showed an increasing tendency of the saturation magnetization with grain size, which is attributed to crystallinity increase in the grains. The $M-H$ hysteresis loop results showed a transition from disordered-to-ordered magnetism which belongs to different magnetically dominant stages of formation. The starting appearance of room temperature ferromagnetic order suggested by the sigmoid-shaped loops seems to be dependent on crystallinity, phase purity and a sufficient number of large enough magnetic domain-containing grains having been formed in the microstructure. An increasing trend of transmission loss with grain size may be attributed to increment of loss contribution from hysteresis and domain wall resonance of the samples. The changes in crystallinity and microstructure, and the associated processes of microwave resonance and relaxation due to domain wall movements and damping of spin rotation contributes to the variations in transmission loss and ferromagnetic linewidth of the samples. The increased electrical resistivity while the microstructure was evolving is believed to strongly indicates improved phase purity and compositional stoichiometry.