## Proton (H<sup>+</sup>) transport properties of CMC–PVA blended polymer solid electrolyte doped with NH<sub>4</sub>NO<sub>3</sub>

M.A. Saadiah<sup>a,c</sup>, Y. Nagao<sup>b</sup>, A.S. Samsudin<sup>c</sup>

<sup>a</sup> Department of Chemistry, Centre for Foundation Studies, International Islamic University Malaysia, 26300 Gambang, Pahang, Malaysia

<sup>b</sup> School of Materials Science, Japan Advanced Institute of Science and Technology, 1-1 Asahidai, Nomi, Ishikawa 923-1292, Japan

<sup>c</sup> Ionic Materials Team, Faculty of Industrial Sciences and Technology, Universiti Malaysia Pahang, 26300 Pahang, Malaysia

## ABSTRACT

This present work investigated the proton  $(H^{+})$  conduction behavior of the blended polymer solid electrolyte (BPSE) derived from carboxymethyl cellulose (CMC) and polyvinyl alcohol (PVA) that was doped with ammonium nitrate ( $NH_4NO_3$ ). The properties of this CMC-PVA-AN BPSE were evaluated using Fourier transform infrared spectroscopy (FTIR), transference number measurement (TNM), thermal gravimetric analysis (TGA), differential scanning calorimetry (DSC), X-ray diffraction (XRD), scanning electron microscopy (SEM), and electrical impedance spectroscopy (EIS). We found that doping (NH<sub>4</sub>NO<sub>3</sub>) improved the chemical and thermal stability of the CMC-PVA BPSE. The highest ionic conductivity was  $(~10^{-3} \text{ S/cm})$  of the BPSE at ambient temperature achieved with a CMC:PVA:NH<sub>4</sub>NO<sub>3</sub> composition of 56:14:30 wt%. This was due to the interplay of segmental motion between the CMC and PVA and also the  $H^{+}$  hopping mechanism as revealed by FTIR. XRD and morphology analysis showed that the peak intensity decreased which implied an increase in its amorphous nature. Based on the transport properties, the CMC-PVA-AN BPSE conduction mechanism was governed by number of ions, ionic mobility and also free ions diffusion coefficient. The proton transference number (tH+= 0.42) in the present study indicated that the charge transport in the BPSE was predominantly due to the H<sup>+</sup> carrier conduction.

## KEYWORDS

Blended polymer; Conductivity; Transport properties; Proton (H<sup>+</sup>) carrier

## ACKNOWLEDGMENTS

The authors would like to thank Ministry of Higher Education, Malaysia (MOHE) for FRGS grant (RDU1901114) and Universiti Malaysia Pahang for internal grant (RDU190389) and UMP postgraduate financial assistant (PGRS190307), Faculty Industrial Science & Technology, Universiti Malaysia Pahang for the technical and research support.