

INVESTIGATION ON MECHANICAL
PROPERTIES OF LIGHTWEIGHT
AGGREGATE CONCRETE CONTAINING
COAL ASH AS PARTIAL SAND
REPLACEMENT

AISYAH AQILAH BINTI AKMAL

B. ENG(HONS.) CIVIL ENGINEERING

UNIVERSITI MALAYSIA PAHANG



STUDENT'S DECLARATION

I hereby declare that the work in this thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Malaysia Pahang or any other institutions.

(Student's Signature)

Full Name : AISYAH AQILAH BINTI AKMAL

ID Number : AA15111

Date : 31ST MAY 2019

INVESTIGATION ON MECHANICAL PROPERTIES OF LIGHTWEIGHT
AGGREGATE CONCRETE CONTAINING COAL ASH AS PARTIAL SAND
REPLACEMENT

AISYAH AQILAH BINTI AKMAL

Thesis submitted in fulfillment of the requirements
for the award of the
B. Eng (Hons.) Civil Engineering

Faculty of Civil Engineering and Earth Resources
UNIVERSITI MALAYSIA PAHANG

MAY 2019

ACKNOWLEDGEMENTS

Foremost, I am very grateful to Allah S.W.T and his willingness that allow me to complete this Final Year Project successfully. I would like to express my greatest gratitude to my supervisor, Assoc. Prof. Dr. Khairunisa Muthusamy for the supports in completing my Final Year Project. The opportunity I had in completing this final year project was a great chance for learning and for professional development. Even though there were a lot of circumstances while finishing this project, but all the knowledge, guidance and advises that I got helped me to complete the project successfully.

I would like to express my deepest appreciation to those who provided me the possibility to complete this project. A special gratitude I give to my lab mates, Nur Liyana Hanis binti Hamdan, Nurul Atikah Shafika binti Jamil and Siti Nurdiana binti Jamil whose contribution in time and energy, helped me in conducting laboratory work. A big thanks to all laboratory assistants that help me in operating the machines and ease the process of laboratory works.

Furthermore, I would also like to acknowledge with much appreciation the crucial role of my parent, Puan Asiah Binti Jenon and Encik Akmal bin Hussein for providing me with unfailing supports and continuous encouragement throughout my years of study. Last but not least, many thanks go to all of my beloved friends who have helped me to answer my question regarding any problem-related in preparing this project successfully.

I perceive as this opportunity as a big milestone in my future development. I will strive to use my gained skills and knowledge in the best possible way. I hope to continue cooperation with all of you in the future.

ABSTRAK

Peningkatan permintaan dalam penggunaan elektrik dan pengeluaran dari industri kelapa sawit telah menyumbang kepada peningkatan pengeluaran bahan buangan. Permintaan tinggi arang batu oleh loji kuasa, meningkatkan pengeluaran abu arang batu. Malaysia sebagai pengeksport minyak kelapa sawit terbesar dunia juga telah menghasilkan sejumlah besar sisa pepejal dan boleh menjadi punca masalah persekitaran. Selain daripada meluaskan tapak pelupusan yang ada, penggunaan bahan buangan adalah sangat berguna kerana memerlukan kos yang lebih rendah. Oleh itu, penggunaan bahan buangan dalam industri pembinaan meningkatkan peluang dalam menyelesaikan masalah persekitaran. Dalam kajian ini, siasatan telah dijalankan untuk mengetahui kekuatan mampatan, kekuatan lenturan dan modulus keanjalan konkrit agregat ringan yang mengandungi abu dasar arang batu sebagai pengganti pasir separa. Permukaan tepu kering tempurung kelapa sawit digunakan sebagai agregat kasar. Abu dasar arang batu digunakan sebagai pengganti pasir separa untuk 0%, 10%, 20% dan 30%. Semua konkrit diawet dengan kaedah awetan udara. Ujian kekuatan mampatan dan ujian kekuatan lentur dilakukan pada 7 hari, 28 hari dan 60 hari. Sementara itu, modulus ujian keanjalan dilakukan pada 28 hari. Berdasarkan tiga ujian yang dijalankan, boleh dibuat kesimpulan bahawa kekuatan maksimum konkrit mencapai 10% penggantian pasir oleh abu dasar arang batu. Kekuatan konkrit mula berkurang dengan peningkatan peratusan abu dasar arang batu. Sebagai kesimpulan, penggantian optimum abu dasar arang batu boleh digunakan untuk menghasilkan kekuatan konkrit yang lebih tinggi.

ABSTRACT

The increasing demand for electricity consumption and the production from oil palm industry have contributed to increasing the production of waste materials. The high demand for coal by power plants, increase the production of coal ash. Malaysia as the world largest exporter of oil palm shell also have produced a vast amount of solid waste and can be a cause of the environmental problem. Instead of expanding the available landfill, the utilization of the waste materials would be very useful since it required a lesser cost. Rather than that, utilization of these waste materials in construction industry increase chances in solving environment problem. In this study, investigations have been carried out in order to figure out the compressive strength, flexural strength, and modulus of elasticity of oil palm shell lightweight concrete containing coal bottom ash as partial sand replacement. Saturated surface dry oil palm shell was used as coarse aggregate in the concrete. Coal bottom ash was used as partial sand replacement for 0%,10%, 20%, and 30%. All specimens were subjected to air curing method. The compressive strength test and flexural strength test were conducted at 7-day, 28-day, and 60-day. Meanwhile, modulus of elasticity tests was conducted at 28-day. Based on the three tests conducted, it can be concluded that the strength of the concrete reaches the maximum with 10% partial replacement of sand by coal bottom ash. The strength of the concrete started to decrease with increasing percentage replacement of coal bottom ash. As a conclusion, the optimum replacement of coal bottom ash can be used to produce higher concrete strength.

TABLE OF CONTENT

DECLARATION	
TITLE PAGE	
ACKNOWLEDGEMENTS	ii
ABSTRAK	iii
ABSTRACT	iv
TABLE OF CONTENT	v
LIST OF TABLES	viii
LIST OF FIGURES	ix
LIST OF SYMBOLS	xi
LIST OF ABBREVIATIONS	xii
CHAPTER 1 INTRODUCTION	1
1.1 Background of the Study	1
1.2 Problem Statement	2
1.3 Objectives of the Study	3
1.4 Scope of Research	3
1.5 Significance of Research	3
1.6 Layout of Thesis	4
CHAPTER 2 LITERATURE REVIEW	5
2.1 Introduction	5
2.2 Mixing Ingredients of Lightweight Aggregate Concrete	6
2.2.1 Ordinary Portland Cement	6

2.2.2	Lightweight Aggregate	8
2.2.3	Superplasticizer	9
2.2.4	Sand	10
2.2.5	Water	11
2.3	Mechanical Properties of Lightweight Aggregate Concrete	12
2.3.1	Compressive Strength	12
2.3.2	Flexural Strength	14
2.3.3	Modulus of Elasticity	16
2.4	Sand Mining	18
2.4.1	Sand Industry	18
2.4.2	Environmental Impacts	18
2.5	Oil Palm Shell	20
2.5.1	Production of Oil Palm Shell	20
2.5.2	Effect to Environment	21
2.5.3	Uses of Oil Palm Shell	21
2.6	Coal Bottom Ash	23
2.6.1	Production of Coal Bottom Ash	23
2.6.2	Environmental Effect	25
2.6.3	Uses of Coal Bottom Ash	25
CHAPTER 3 METHODOLOGY		27
3.1	Introduction	27
3.2	Materials Used	28
3.2.1	Ordinary Portland cement	28
3.2.2	Oil Palm Shell	29
3.2.3	Coal Bottom Ash	32

3.2.4	Sand	34
3.2.5	Superplasticizer	36
3.2.6	Water	36
3.3	Mix Proportion	37
3.4	Concrete Preparation	38
3.5	Laboratory Testing	41
3.5.1	Compressive Strength Test	41
3.5.2	Flexural Strength Test	43
3.5.3	Modulus of Elasticity Test	45
CHAPTER 4 RESULTS AND DISCUSSION		47
4.1	Introduction	47
4.2	Compressive Strength	48
4.3	Flexural Strength	51
4.4	Modulus of Elasticity	54
CHAPTER 5 CONCLUSION		55
5.1	Introduction	55
5.2	Conclusion	55
5.3	Recommendation	56
REFERENCES		57

LIST OF TABLES

Table 2.1	Chemical properties of ordinary Portland cement	7
Table 2.2	Compressive strength of oil palm shell concrete under the air-curing condition	13
Table 2.3	28-day hardened concrete properties	16
Table 2.4	Classification of pollution, pollutants and source of pollutants	21
Table 2.5	Properties of the crushed granite (conventional aggregate) and oil palm shell	23
Table 2.6	Chemical composition of coal bottom ash	25
Table 3.1	Properties of oil palm shell coarse aggregate	29
Table 3.2	Properties of coal bottom ash as sand replacement	33
Table 3.3	Properties of sand used in concrete mixes	34
Table 3.4	Proportion of plain and coal bottom ash concrete mixes (1 m ³)	38

LIST OF FIGURES

Figure 2.1	Compressive strength of concrete with coal bottom ash as partial sand replacement	14
Figure 2.2	Flexural strength of concrete with coal bottom ash as partial sand replacement	15
Figure 2.3	Relation between one-day unit density and 28 days modulus of elasticity of coal bottom ash concrete	17
Figure 2.4	Illegal sand extraction in 1988 and its effect 5 years later	19
Figure 2.5	World palm oil production in 2011	20
Figure 2.6	Oil palm shell coarse aggregate	22
Figure 2.7	The scanning electron micrograph of coal bottom ash	24
Figure 3.1	Ordinary Portland cement	28
Figure 3.2	Collecting oil palm shell	30
Figure 3.3	Oven-dried oil palm shell was soaked for 24 hours prior to casting	31
Figure 3.4	Oil palm shell was collected after air-dried for 1 hour	31
Figure 3.5	The saturated surface dry condition of oil palm shell	32
Figure 3.6	Sieve work on coal bottom ash	33
Figure 3.7	Coal bottom ash that has been sieved	34
Figure 3.8	River sand is stored outside the Concrete Laboratory	35
Figure 3.9	River sand used in concrete mix	35
Figure 3.10	Superplasticizer used to increase the workability of concrete	36
Figure 3.11	Tap water used in the concrete mix	37
Figure 3.12	All materials were mixed in the drum mixer	39
Figure 3.13	The fresh concrete readily placed inside the mold	39
Figure 3.14	Fresh concrete was poured into the beam mold	40
Figure 3.15	Fresh concrete was placed into the mold before compaction	40

Figure 3.16	Compressive strength testing machine	42
Figure 3.17	Cube specimen after undergo compressive strength test	42
Figure 3.18	Flexural machine	44
Figure 3.19	Specimen was put at the machine for flexural strength test	44
Figure 3.20	Beam specimen reaches maximum loading	45
Figure 3.21	Machine to conduct modulus of elasticity test	46
Figure 3.22	Cylinder specimen after modulus of elasticity test had been conducted	46
Figure 4.1	The compressive strength of oil palm shell concrete containing coal bottom ash up to 60 days	49
Figure 4.2	Compressive strength of oil palm shell concrete at 7-days	49
Figure 4.3	Compressive strength of oil palm shell concrete at 28-days	50
Figure 4.4	Compressive strength of oil palm shell concrete at 60-days	50
Figure 4.5	The flexural strength of oil palm shell concrete with coal bottom ash up to 60 days	51
Figure 4.6	Flexural strength of oil palm shell concrete at 7-days	52
Figure 4.7	Flexural strength of oil palm shell concrete at 28-days	52
Figure 4.8	Flexural strength of oil palm shell concrete at 60-days	53
Figure 4.9	Modulus of elasticity of oil palm shell concrete at 28-days	54

LIST OF SYMBOLS

P	The maximum load at failure
A	The cross-sectional area of cube
f_{cf}	Flexural strength
F	Maximum Load
ℓ	Distance between supporting rollers
d_1, d_2	The lateral dimensions of the specimens

LIST OF ABBREVIATIONS

MgO	Magnesium Oxide
C ₃ S	Tricalcium Silicate
C ₂ S	Dicalcium Silicate
C ₃ A	Tricalcium Aluminate
C ₄ AF	Tetra calcium Aluminoferrite
CO ₂	Carbon Dioxide
SiO ₂	Silica
Fe ₂ O ₃	Ferric Oxide
CaO	Calcium Oxide
K ₂ O	Potassium Oxide
P ₂ O ₅	Phosphorus Pentoxide
SO ₃	Sulphur Trioxide
SrO	Strontium Oxide
Al ₂ O ₃	Aluminium Oxide
Cl	Chloride
LOI	Loss on ignition

CHAPTER 1

INTRODUCTION

1.1 Background of the Study

Nowadays, concrete is an important element in the construction of a building. In the 21st century, 11 billion people will be living on the earth and that clearly proves that as the population increases, the more common goods and services are needed. Meanwhile, agricultural wastes and solid material disposal are giving serious damage to the environment. Since Malaysia recorded as the highest amount of solid waste produced through palm oil industry in a year which is 47 million tonnes, to some extent, it can be the cause of the environmental problem (Pordesari, et al., 2016). In countries, where abundant agricultural wastes are discharged, these wastes can be used as potential materials or replacement material in the construction industry. The oil palm shell is one of the wastes and has potential to be used as coarse aggregate in concrete (Mannan and Ganapathy, 2002). Oil palm shell had been successfully used as lightweight coarse aggregate in order to achieve the structural grade lightweight concrete and high strength lightweight oil palm shell concrete (Islam et al., 2016).

Coal ash is residue resulting from the combustion of pulverized coal or lignite in a thermal power plant. The burnt coal produces smoke which goes into the air is captured as fly ash, meanwhile, the burnt coal at the bottom of the burning chamber that is cooled is called bottom ash. There is six thermal power plant operated in Malaysia with an annual coal consumption of 24.7 million tonnes. The production of coal and wastes are increasing due to the high demand for coal consumption. Coal-fired plants generate waste by-product such as coal bottom ash through the generation of electricity is normally sent to landfill. Therefore, an excessive amount of waste should be used to produce concrete

that is lightweight, economic and environmental friendly towards the sustainable production in the construction industry (Sadon, et al., 2017).

1.2 Problem Statement

Malaysia as the world's largest exporter of palm oil, facing problem in the processing of palm oil that produced a large amount of by-product such as oil palm shell. In 2011, 18 million tonnes of palm oil products were exported. Malaysia produces 18.79 million tonnes of crude palm oil on roughly 5 million hectares of land (Yew, et al., 2014). This by-product is one of the main contributors to the pollution problem. A large amount of oil palm shell waste materials is stockpiled and dumped. Oil palm shell is generated approximately 6.89 million tonnes every year (Muthusamy and Zamri, 2016). These have created a major disposal problem (Abdullah and Sulaiman, 2013). This large amount of waste material produced should be used as an alternative to producing lightweight concrete.

Other than that, a fast-developing country with thriving economies has increased demand for the use of electricity in Malaysia. Tenaga Nasional Berhad (TNB) consumed 1.5 million tonnes of coal each year. Meanwhile, in 2016, peninsular Malaysia recorded as 29 million tonnes of annual coal consumption of power sector (Sadon, et al., 2017). Coal bottom ash that is generated from electricity generation by the coal-fired plant will be sent to landfills. Disposal of coal bottom ash has become a major problem due to insufficient dumping sources and cause environmental hazards (Singh and Siddique, 2013). The production of coal bottom ash increased as well as the consumption of coal by power plants increases.

1.3 Objectives of the Study

The objectives of this study are to:

- i. To determine the compressive strength of oil palm shell lightweight concrete using containing coal bottom ash as partial sand replacement.
- ii. To determine the flexural strength of oil palm shell lightweight concrete using containing coal bottom ash as partial sand replacement.
- iii. To determine the modulus of elasticity of oil palm shell lightweight concrete using containing coal bottom ash as partial sand replacement.

1.4 Scope of Research

The scope of this study focused on the alternatives to produce lightweight concrete using oil palm shell as coarse aggregate containing coal bottom ash as partial replacement of sand at different percentage replacement 0%, 10%, 20% and 30% of the sand volume. This study used characteristics of the concrete grade of 30 MPa. Oil palm shell was chosen to be the waste material to be used to produce lightweight concrete. This study also focused on using air type curing. The compressive and flexural strength of the concrete was tested at the days of 7, 28 and 60 days, meanwhile, the modulus of elasticity of the concrete was tested at 28-day based on curing period. The tests were carried out in Concrete Laboratory in Universiti Malaysia Pahang.

1.5 Significance of Research

Since the production of coal bottom ash and oil palm shell are increasing, the utilization of the waste materials would be very useful instead of expanding the available landfill. Utilization of these industrial by-products would be economical rather than expanding the landfill that probably needs much cost. The higher production rate of the waste makes it necessary to reuse the wastes for sustainability. Besides the environmental problem can be solved, it is significant to grab the opportunity especially in the construction industry as their large amount of production.

REFERENCES

- Abdullah, N. and Sulaiman, F. (2013) 'The Oil Palm Wastes in Malaysia', *Biomass Now - Sustainable Growth and Use*, (December). doi: 10.5772/55302.
- Argiz, C. and Moragues, A. (2018) 'Use of ground coal bottom ash as cement constituent in concretes exposed to chloride environments', 170, pp. 25–33. doi: 10.1016/j.jclepro.2017.09.117.
- Ashraf, M. A., Maah, M. J. and Yusoff, I. (2011) 'Sand mining effects, causes, and concerns: A case study from Bestari Jaya, Selangor, Peninsular Malaysia', 6(6), pp. 1216–1231.
- Aslam, M., Shafigh, P. and Jumaat, M. Z. (2015) 'Structural Lightweight Aggregate Concrete by Incorporating Solid Wastes as Coarse Lightweight Aggregate', *Applied Mechanics and Materials*, 749(March), pp. 337–342. doi: 10.4028/www.scientific.net/AMM.749.337.
- Aswathy, P. U. and Paul, M. M. (2015) 'Behaviour of Self Compacting Concrete by Partial Replacement of Fine Aggregate with Coal Bottom Ash', 2(October 2015), pp. 45–52.
- Ayub, T., Khan, S. U., and Memon, F. A. (2014) 'Mechanical characteristics of hardened concrete with different mineral admixtures: A review', *The Scientific World Journal*, 2014. doi: 10.1155/2014/875082.
- Dawood, E. T., and Ramli, M. (2008) 'Rational Mix Design of Lightweight Concrete for Optimum Strength', *Built Environment in Developing Countries*, (ICBEDC), pp. 515–526.
- Islam, U., Mo, K. H., and Alengaram, U. J. (2016) 'Mechanical and fresh properties of sustainable oil palm shell lightweight concrete incorporating palm oil fuel ash', *Journal of Cleaner Production*. Elsevier Ltd, 115, pp. 307–314. doi: 10.1016/j.jclepro.2015.12.051.
- Jayaranjan, M. L. D., van Hullebusch, E. D. and Annachhatre, A. P. (2014) 'Reuse options for coal-fired power plant bottom ash and fly ash', *Reviews in Environmental Science and Biotechnology*, 13(4), pp. 467–486. doi: 10.1007/s11157-014-9336-4.
- Kumar, P. S., Babu, M. J. R. K. and Kumar, K. S. (2016) 'Experimental Study on Lightweight Aggregate', (February).

Mannan, M. A., and Ganapathy, C. (2004) 'Concrete from an agricultural waste-oil palm shell (OPS)', 39, pp. 441–448. doi: 10.1016/j.buildenv.2003.10.007.

Mannan, M. A. and Ganapathy, C. U. (2002) 'Engineering properties of concrete with oil palm shell as coarse aggregate'.

Meghashree, M. (2016) 'Comparison of Physical Properties between Natural Sand and Manufactured Sand', 3(07), pp. 92–96.

Mo, K. H., Alengaram, U. J. and Jumaat, M. Z. (2015) 'Experimental investigation on the properties of lightweight concrete containing waste oil palm shell aggregate', *Procedia Engineering*. Elsevier B.V., 125, pp. 587–593. doi: 10.1016/j.proeng.2015.11.065.

Muthusamy, K. and Zamri, N. A. (2016) 'Mechanical Properties of Oil Palm Shell Lightweight Aggregate Concrete Containing Palm Oil Fuel Ash as Partial Cement Replacement', 20, pp. 1473–1481. doi: 10.1007/s12205-015-1104-7.

National Ready Mixed Concrete Association (2000) 'CIP 16 - Flexural Strength Concrete'.

Neville, A. M. (2011) *Properties of concrete*. 5th edition. Pearson Education limited.

Pordesari, A. J., Salleh, S. and Shafigh, P. (2016) 'Toward Sustainability in Concrete Industry by Using Of Solid Wastes from Palm Oil Industry', *International Building Control Conference (IBCC)*, 00099, pp. 1–10. doi: 10.1051/mateconf/20166600099.

River Sand Mining Management Guideline (2009). Department of Irrigation and Drainage (DID).

Sadon, S. N., Beddu, S. and Naganathan, S. (2017) 'Coal Bottom Ash as Sustainable Material in Concrete – A Review', 10(September). doi: 10.17485/ijst/2017/v10i36/114595.

Shafigh, P. *et al.* (2014) 'Structural lightweight aggregate concrete using two types of waste from the palm oil industry as aggregate', 80, pp. 187–196. doi: 10.1016/j.jclepro.2014.05.051.

Shafigh, P., Jumaat, M. Z. and Mahmud, H. (2011a) 'A new method of producing high strength oil palm shell lightweight concrete', *Materials and Design*. Elsevier Ltd, 32(10), pp. 4839–4843. doi: 10.1016/j.matdes.2011.06.015.

Shafigh, P., Jumaat, M. Z. and Mahmud, H. (2011b) 'Oil palm shell as a lightweight aggregate for production high strength lightweight concrete', *Construction and Building Materials*. Elsevier Ltd, 25(4), pp. 1848–1853. doi: 10.1016/j.conbuildmat.2010.11.075.

Shafigh, P., Mahmud, H. Bin and Jumaat, M. Z. (2012) 'Oil palm shell lightweight concrete as a ductile material', *Materials and Design*. Elsevier Ltd, 36, pp. 650–654. doi: 10.1016/j.matdes.2011.12.003.

Shafigh, P., Nomeli, M. A. and Alengaram, U. J. (2016) 'Engineering properties of lightweight aggregate concrete containing limestone powder and high volume fly ash', *Journal of Cleaner Production*, 135, pp. 148–157. doi: 10.1016/j.jclepro.2016.06.082.

Singh, M. and Siddique, R. (2013) 'Resources, Conservation and Recycling Effect of coal bottom ash as partial replacement of sand on properties of concrete', *Resources, Conservation & Recycling*. Elsevier B.V., 72, pp. 20–32. doi: 10.1016/j.resconrec.2012.12.006.

Singh, M. and Siddique, R. (2014a) 'Compressive strength, drying shrinkage and chemical resistance of concrete incorporating coal bottom ash as a partial or total replacement of sand', *Construction and Building Materials*. Elsevier Ltd, 68, pp. 39–48. doi: 10.1016/j.conbuildmat.2014.06.034.

Singh, M. and Siddique, R. (2014b) 'Strength properties and micro-structural properties of concrete containing coal bottom ash as partial replacement of fine aggregate', *Construction and Building Materials*. Elsevier Ltd, 50, pp. 246–256. doi: 10.1016/j.conbuildmat.2013.09.026.

Singh, M. and Siddique, R. (2016) 'Effect of coal bottom ash as partial replacement of sand on workability and strength properties of concrete', *Journal of Cleaner Production*. Elsevier Ltd, 112, pp. 620–630. doi: 10.1016/j.jclepro.2015.08.001.

Singh, N., Mithulraj, M. and Arya, S. (2018) 'Resources, Conservation & Recycling Influence of coal bottom ash as a fine aggregate replacement on various properties of concretes : A review', 138(July), pp. 257–271. doi: 10.1016/j.resconrec.2018.07.025.

Teo, F. Y., Noh, M. N. M. and Ghani, A. A. (2017) 'River Sand Mining Capacity in Malaysia', *Proceedings of the 37th IAHR World Congress*, 6865(5), pp. 538–546.

Traore, Y. B., Messan, A. and Hannawi, K. (2018) 'Effect of oil palm shell treatment on the physical and mechanical properties of lightweight concrete', *Construction and Building Materials*. Elsevier Ltd, 161, pp. 452–460. doi: 10.1016/j.conbuildmat.2017.11.155.

Yew, M. K., Mahmud, H. Bin and Ang, B. C. (2014) 'Effects of heat treatment on oil palm shell coarse aggregates for high strength lightweight concrete', *Materials and Design*. Hindawi Publishing Corporation, 54(May), pp. 702–707. doi: 10.1016/j.matdes.2013.08.096.