## Enhancing the materials circularity: from laboratory waste to electrochemical capacitors

B. Pal<sup>ab</sup>, A. Yasin<sup>ac</sup>, V. Sunil<sup>ac</sup>, Z. Sofer<sup>b</sup>, C.-. Yang<sup>def</sup>, **R. Jose<sup>ac</sup>** 

 <sup>a</sup> Center for Intelligent Materials, Universiti Malaysia Pahang, 26300, Gambang Kuantan, Malaysia
<sup>b</sup> Department of Inorganic Chemistry, University of Chemistry and Technology Prague, 166 28, Prague 6, Czech Republic
<sup>c</sup> Faculty of Industrial Sciences and Technology, Universiti Malaysia Pahang, 26300, Gambang Kuantan, Malaysia
<sup>d</sup> Battery Research Center of Green Energy, Ming Chi University of Technology, New Taipei City, 24301, Taiwan, ROC
<sup>e</sup> Department of Chemical Engineering, Ming Chi University of Technology, New Taipei City, 24301, Taiwan, ROC
<sup>f</sup> Department of Chemical and Materials Engineering, and Green Technology Research Center, Chang Gung University, Taoyuan City, 333, Taiwan, ROC

## ABSTRACT

Enhancing the circularity of materials is at the forefront of sustainability; this paper addresses smart reuse of a laboratory waste, i.e., paper towels, as one of the main components (electrodes) in an energy storage device (electrochemical capacitor, EC). We obtained carbon from wastepaper towels by converting them into cellulose through alkali treatment, subsequent enhancement of porosity via nitric acid reflux, and enhancement of chemical purity via controlled annealing. The porous carbon thereby optimized is characterized for chemical structure, surface structure, and morphology as well as electrochemical charge storability. The carbon sample obtained at 800 °C showed graphitization and interconnected morphology displaying a combination of micro and mesopores, superior surface area ( $\sim$ 528  $m^{2}/g$ ), desirable pore diameter for efficient ion adsorption (~3.3 nm), and specific capacitance ~230 F/g in 1 M KOH and ~160 F/g in 1 M Na<sub>2</sub>SO<sub>4</sub> electrolytes. Symmetrical electrochemical capacitors are also fabricated using the best performing carbon electrode in the above two electrolytes, which delivered desirable specific energy and specific power with high cycling stability. Given the longer cycling stability of the device and considering the acceptable properties, the present work is a way forward for enhancing the circularity of the laboratory wastepaper towels.

## **KEYWORDS**

Cellulose–carbon conversion; Circular economy; Electrochemical double layer capacitor; Materials sustainability; Supercapacitor

## ACKNOWLEDGMENTS

This project is funded by Universiti Malaysia Pahang through RDU203301. Bhupender Pal and Amina Yasin would like to acknowledge the Research & Innovation Department of Universiti Malaysia Pahang (<u>http://ump.edu.my</u>) for the award of Postdoctoral Fellowship.