



Improvement in stability and thermophysical properties of CNC-MXene nanolubricant for Tribology application

Mohd Kamal Kamarulzaman^a, Sakinah Hisham^{a,b}, Kumaran Kadirgama^{a,b},
Devarajan Ramasamy^c, M. Samykano^{b,*}, Zafar Said^{d,h,i,*}, A.K. Pandey^{e,f,g}

^a Advanced Nano Coolant-Lubricant (ANCL) Lab, Automotive Engineering Centre, Universiti Malaysia Pahang, 26600 Pekan, Pahang, Malaysia

^b Faculty of Mechanical and Automotive Engineering Technology, Universiti Malaysia Pahang, 26600 Pekan, Pahang, Malaysia

^c Center of Excellence for Advanced Research in Fluid Flow

^d Department of Sustainable and Renewable Energy Engineering, University of Sharjah, 27272 Sharjah, United Arab Emirates

^e Research Centre for Nano-Materials and Energy Technology (RCNMET), School of Engineering and Technology, Sunway University, 47500 Selangor Darul Ehsan, Malaysia

^f Center for Transdisciplinary Research (CFTR), Saveetha Institute of Medical and Technical Services, Saveetha University, Chennai, India

^g CoE for Energy and Eco-Sustainability Research, Uttaranchal University, Dehradun, India

^h U.S.-Pakistan Center for Advanced Studies in Energy (USPCAS-E), National University of Sciences and Technology (NUST), Islamabad, Pakistan

ⁱ Department of Industrial and Mechanical Engineering, Lebanese American University (LAU), Byblos, Lebanon

ARTICLE INFO

Keywords:

Hybrid nanolubricant
Cellulose nanocrystal
MXene
Viscosity
Thermal conductivity

ABSTRACT

The primary objective of the present work is to carry out an experimental study into the stability and thermophysical characteristics of cellulose nanocrystal, MXene, and hybrid cellulose nanocrystal-MXene added to engine oil as a lubricant for piston ring-cylinder liner application. There have been experiments with stability techniques like sedimentation observation, UV-visible spectroscopy, and zeta potential. Thermophysical characteristics have been measured using the viscosity index, dynamic viscosity, and thermal conductivity at various concentrations (ranging from 0.01 % to 0.05 %) and temperatures (from 40 °C to 100 °C). Even without any surfactants, the cellulose nanocrystal-MXene nanolubricants showed good dispersion during the first seven days. The results of the ultraviolet-visible spectrophotometer indicate that cellulose nanocrystal nanolubricants exhibit an absorbance ratio that is most similar to one. It can be shown that the zeta potential increases with a concentration in the distribution of cellulose nanocrystal, MXene, and cellulose nanocrystal-MXene nanoparticles. According to the viscosity index results, all nanolubricants reduce the lubricity oil's viscosity by 16.77 % to 20.33 %, with cellulose nanocrystal-MXene showing the greatest improvement at 0.05 %. At solid concentrations of 0.01 % cellulose nanocrystal and 0.05 % cellulose nanocrystal-MXene with temperatures of 40 °C and 90 °C, the dynamic viscosity was enhanced by 0.92 % and 130.87 %, respectively. The solid concentration of 0.05 % cellulose nanocrystal-MXene was determined to have the greatest effect on the thermal conductivity ratio of the chosen nanolubricant at 90 °C. Overall, at an average concentration of 0.05 %, the thermophysical properties' performance was increased by the addition of cellulose nanocrystal-MXene nanoparticle. The study's findings may be useful for applications involving heat transmission, particularly tribological ones.

1. Introduction

Current machinery and its whole system must be scaled above standard design parameters to increase total production at the lowest input cost. Tribology significantly improves machinery and internal combustion (IC) engine efficiency and aids in extending the life of moving parts [1]. Nearly 18 % of IC engines' ideal power is lost due to

friction and hazardous exhaust emissions [2]. Reducing frictional losses can improve the IC engine's performance and fuel efficiency [3]. Therefore, efficient self-lubricating coatings [4] or lubrication [5,6] are compulsory for automotive engines, which presents a challenge to researchers and designers.

Numerous research teams have also evaluated the thermophysical and performance characteristics of nanolubricants used in engines [7-9].

* Corresponding authors.

E-mail addresses: mahendran@ump.edu.my (M. Samykano), zsaid@sharjah.ac.ae, zaffar.ks@gmail.com (Z. Said).

<https://doi.org/10.1016/j.molliq.2023.121695>

Received 15 August 2022; Received in revised form 16 February 2023; Accepted 19 March 2023

Available online 28 March 2023

0167-7322/© 2023 Elsevier B.V. All rights reserved.