INVERSE VULCANISED POLYSULPHIDE ADSORBENT FROM WASTE COOKING PALM OIL FOR Cu²⁺ REMOVAL

MOHD FAIZAL ALI¹; NANCY NUBUR LIBAT¹; HANNAH NISA ADAWIYAH¹; ABDULLAH NAYEEM^{1,2} and JUN HASLINDA SHARIFFUDDIN^{1,3*}

ABSTRACT

Heavy metals are considered to be toxic to humans. Commonly produced by petrochemical plants and pesticide productions, various techniques have been utilised to treat wastewater contaminated with heavy metal such as copper (Cu^{2+}). This article focuses on using adsorption by utilising polysulphide adsorbent to treat wastewater via inverse vulcanisation. The huge amount of waste cooking palm oil (WCO) that is generated daily in Malaysia has motivated the study to produce a low-cost adsorbent with high removal efficiency. The polysulphide adsorbent was prepared with sulphur powder and waste cooking oil with a ratio of 9:1. The effect of contact time, initial Cu^{2+} concentration, and adsorbent dosage were studied using a batch adsorption process. The highest removal efficiency was 77.81% obtained while using 5 g of adsorbent dosage to treat 5 mg/L of Cu^{2+} aqueous solution. The Freundlich and Langmuir isotherm was used for modelling Cu^{2+} adsorption in an aqueous medium which was modelled best by the Langmuir isotherm. Overall, these results confirmed polysulphide as a low-cost and potential adsorbent to remove Cu^{2+} from wastewater.

Keywords: heavy metal removal, inverse vulcanisation, polysulphide adsorbent, waste cooking palm oil, waste to wealth.

Received: 27 July 2023; Accepted: 27 November 2023; Published online: 29 January 2024.

INTRODUCTION

The adverse effects of heavy metal wastewater on human health and the aquatic system have concerned the scientific community. Heavy metal wastewater is toxic and carcinogenic in nature and sometimes is released without prior wastewater treatment. Globally, almost 78% of heavy metal wastewater remains untreated, which bioaccumulates along the food chain because of its non-degradable nature (Jones *et al.*, 2021; Kumar *et al.*, 2019; Worthington *et al.*, 2017). Copper

³ Centre for Sustainability of Mineral and Resource Recovery Technology (Pusat SMaRRT), Universiti Malaysia Pahang Al-Sultan Abdullah, Lebuh Persiaran Tun Khalil Yaakob, 26300 Kuantan, Pahang, Malaysia.

 (Cu^{2+}) , an important micronutrient element, has a crucial role in bone formation with the help of enzymes and proteins, but extreme intake of this heavy metal wastewater can lead to brutal health damage including renal and hepatic damage, widespread capillary damage, mucosal irritation and corrosion, severe gastrointestinal and central nervous system irritation, and necrotic changes in the kidney and liver (Arbabi & Golshani, 2016). Highly concentrated Cu²⁺ wastewater damages the osmoregulatory mechanism of the freshwater resources which also endangers the living organisms of the freshwater ecosystem. Different industries such as paint and pigments, metal plating and cleaning, petroleum refineries, smelting, mining, wood pulp, paper board and fertiliser production are responsible for Cu2+ wastewater (Braga & Ricardo, 2021). Ion exchange, coagulation and precipitation, membrane filtration, distillation, reverse osmosis and adsorption have been explored so far to remove Cu²⁺ from aqueous solution (Ramos et al., 2016; Rashed et al., 2023). To deal with Cu²⁺ wastewater, the adsorption process has been proven as an effective method (Ciobanu et al., 2023). However, the high price and

¹ Faculty of Chemical and Process Engineering Technology, Universiti Malaysia Pahang Al-Sultan Abdullah, Lebuhraya Persiaran Tun Khalil Yaakob, 26300 Gambang, Kuantan, Pahang, Malaysia.

² Department of Soil Sciences and Agri-food Engineering, Université Laval, Quebec, QC, G1V 0A6 Canada.

Corresponding e-mail: junhaslinda@umpsa.edu.my

the nature of metal selectivity of the commercial adsorbents have caused some difficulties in the application of commercial adsorbents for Cu^{2+} wastewater adsorption (Emenike *et al.*, 2022).

Recently, inverse vulcanised polysulphides have been used as adsorbents to remove heavy metals in wastewater (Nayeem et al., 2023). Inverse vulcanisation utilises the surplus amount of elemental sulphur obtained from sour gas and refinery treatment plants all over the world exceeding almost 70 million tonnes per year (Nayeem et al., 2022a). Inverse vulcanisation enabled the use of a wide range of crosslinking monomers, which include cooking oils, agro-wastes, inorganic refinery by-products, etc. (Chalker et al., 2019). The vinylic double bonds in the monomers break down during inverse vulcanisation and react with sulphur to form sustainable polysulphides (Chalker et al., 2019). A recent investigation done by Nayeem et al. (2022b) showed the use of waste cooking palm oil (WCO) in inverse vulcanisation, which created a new way to deal with the threat of environmental hazards caused by WCO (Nayeem et al., 2022b). The use of different crosslinkers, simple synthesis process, and high selectivity towards heavy metals have made the inverse vulcanised polysulphide adsorbents suitable for heavy metal wastewater treatment (Chalker et al., 2021; Nayeem et al., 2022a).

Polysulphide was prepared in the current study from sulphur and WCO to remove Cu²⁺ ions. The ratio of sulphur to WCO was 9:1. The characterisation of polysulphides was done using FTIR, TGA, and SEM-EDX to understand the functional bonds, thermal and morphological characteristics. The Cu²⁺ removal was studied by varying the parameters including dosages, initial Cu²⁺ concentration, and contact time. Later, isothermal studies were done by Langmuir and Freundlich isothermal models.

MATERIALS AND METHODS

Materials

Sulphur powder (Sigma Aldrich, USA, S₈ reagent grade sublimed powder, ±99.5%), sodium chloride (NaCl), (Sigma Aldrich, USA, ACS reagent, ≥99.5%), copper nitrate [Cu(NO₃)₂], (Merck, Germany, >230 mesh ASTM) were used as received for polysulphide preparation and Cu²⁺ solution preparation. WCO was sourced from the café of Universiti Malaysia Pahang Al-Sultan Abdullah (UMPSA), Gambang campus and used prior to the removal of existing impurities due to the frying process by 0.224 µm syringe filter. Deionised water (Millipore Elix 5, USA) was produced at the chemical lab (FTKKP), UMPSA.

Polysulphide Synthesis Via Inverse Vulcanisation

The synthesis process was followed by the method done by Abraham et al. (2018) and Naveem et al. (2022b) with some minor modifications (Abraham et al., 2018; Nayeem et al., 2022b). About 9 g of sulphur powder and 3 g of NaCl were weighed according to 3:1 and ground using mortar and pestle to make a fine and homogenous mixture. The mixture was heated in a 50 mL beaker at 195°C and 450 rpm on a hot plate. After 8-10 min the mixture became orange in colour to ensure the complete ring opening of the S-S bond (Chung et al., 2013). Then, WCO of 10 wt.% of sulphur was slowly poured into the mixture using a syringe and heated up for the next 60 min to reach the gel point for successful polymerisation (Gomez et al., 2016). As WCO is not a completely unsaturated vegetable oil, over 9:1 ratio may result in a large amount of unreacted sulphur. This phenomenon was physically observed in a study of the liquid sulphur-oil solution which was not polymerised at all (Worthington et al., 2017). The mixture was then cooled at room temperature for 90 min and ground into a fine powder using a pestle and mortar. The powder was rinsed with deionised water and was stirred at 600 rpm for 30 min to remove the NaCl that was added earlier which acted as porogen. Then the polymer was placed in a vacuum drier for 12 hr at 50°C.

Polysulphide Characterisation

The functional groups of the polysulphides were studied using FTIR with ATR (Thermo Fisher Nicolet iS5, USA) over the range of 400-4,000 cm⁻¹. The thermal stability of the polysulphide was observed through TGA (Hitachi STA7200, Japan) at a constant heating rate of 10°C min⁻¹ from 30°C up to 700°C. Gaseous N₂ was used to create an inert environment. The surface morphology and elemental analyses were studied using scanning electron microscopy (SEM) equipped with an energy dispersive X-ray (EDX) system (Hitachi TM3030 Plus, Japan). During analysis, a platinum (Pt) sputter coat was applied to keep the sample surface uncharged. The main attributes of the adsorbents including the specific surface area, pore size, pore volume and pore distribution were studied through N₂ adsorptiondesorption isotherm by a Micromeritics ASAP 2020 system based on the BET method.

Batch Adsorption of Cu²⁺

A 100 mg L⁻¹ of Cu²⁺ stock solution was prepared in a 50 mL beaker using deionised water (Darweesh *et al.*, 2022). Later, different Cu²⁺ solutions (1, 3 and 5 mg L⁻¹) were prepared through serial dilution to study the effect of initial Cu²⁺ concentration on the adsorption process. Cu²⁺ removal was studied using batch adsorption technique at room temperature. About 100 mL of each concentration was stirred at 450 rpm for 2 hr in a 200 mL beaker. To record the Cu²⁺ concentration of the solution, 2 mL of sample was collected at a regular interval (every 20 min), centrifuged (Thermo Scientific MicroCL 21, USA) and run through atomic absorption spectroscopy (AAS). The effects of the adsorption parameters on Cu²⁺ removal were studied like adsorbent dosages, initial Cu²⁺ concentration and time. Numeric values of these parameters used in this study were varied according to the previous studies (Cheraghipour & Pakshir, 2021; Gonçalves *et al.*, 2021; Stanković et al., 2019). Three different dosages (1, 3 and 5 g 100 mL⁻¹) were used to study the effect of dosages on Cu²⁺ adsorption.

The equilibrium concentration of the adsorbed Cu^{2+} was calculated with the help of Equation (1).

$$q_e = \frac{(C_o - C_e) \times V}{M} \tag{1}$$

Here, q_e denotes adsorption capacity (mg g⁻¹). V stands for the total volume of solution (L) and, M for the mass of adsorbent amount (g). The initial and equilibrium concentration (mg L⁻¹) of Cu²⁺ in solution are denoted respectively by C₀ and C_e. The percentage of Cu²⁺ removal is denoted by R which is calculated using the following Equation (2).

$$R(\%) = \frac{C_o - C_e}{C_o} * 100\%$$
(2)

Adsorption isotherm was analysed using both Langmuir [Equation (3)] and Freundlich [Equation (4)] isothermal model (Ciobanu *et al.*, 2023; Nayeem *et al.*, 2023).

$$\frac{1}{q_e} = \frac{1}{q_m} + \frac{1}{q_m K_L} \frac{1}{C_e}$$
(3)

Here, the maximum possible amount of Cu^{2+} that can be adsorbed per unit mass of adsorbent (mg g⁻¹) and constant for adsorption equilibrium is expressed by q_m and $K_{1/}$ respectively.

$$logq_e = logK_L + \frac{1}{n}logc_e \tag{4}$$

Adsorption intensity for Freundlich isothermal model is denoted by 1/n.

RESULTS AND DISCUSSION

Characterisation of Polysulphide Adsorbent

Generally, FTIR indicates the functional bonds through the characteristic spectral peaks. *Figure 1* shows the FTIR spectra for the synthesised polysulphide compound. The figure depicts the basic characteristic peaks in the spectrum of polysulphide. From the previous study, the characteristic peak at 3,005 cm⁻¹ resembled the vinylic bond of C=C, which was not observed in *Figure 1* and transformed to C-C to form the C-S



Figure 1. FTIR spectra of polysulphides via inverse vulcanisation.

polymeric chain during inverse vulcanisation (Nayeem *et al.*, 2022b). It demonstrates the successful polymerisation of WCO and sulphur. The observations obtained from FTIR follows the similar trends with the previous studies (Gomez *et al.*, 2016; Stanković *et al.*, 2019).

TGA curve showed the decomposition of polysulphide adsorbent in *Figure 2* where at first, the weight decreases slowly. Then, it becomes faster after 200°C. Maximum decomposition was a recorded at 289.6°C with 36.6% mass loss. Generally, WCO shows a single-step degradation. However, polysulphides produced from different vegetable oils through inverse vulcanisation tend to exhibit a two-step degradation (Nayeem *et al.*, 2022b; Tikoalu *et al.*, 2020).



Figure 2. TGA of inverse vulcanised polysulphide adsorbent.

The SEM image of synthesised polysulphide adsorbent with 90 wt.% sulphur has been shown in *Figure 3*. The prepared polysulphide adsorbent has an irregular surface that is shaped like small bricks of different sizes and shapes. The polysulphides present a seemingly rough surface that indicates a high surface area for the adsorption. EDX image presented in *Figure 3*e shows that the percent amount of carbon, oxygen and sulphur composition in the adsorbent is 51.10%, 2.26% and 46.64% respectively.

Effect of Different Parameters

Effect of dosages. The effect of adsorbent dosages on Cu²⁺ removal from wastewater was investigated using three different loadings of polysulphide adsorbents, which were 1, 3 and 5 g respectively. The experiment was conducted at 35°C and a contact time of 120 min with a constant Cu²⁺ initial concentration of 5 mg L⁻¹. The Cu²⁺ removal rate in *Figure 4* indicated an increase in the percentage removal from 41.25%-77.81% as the dosage was increased to 5 g from 1 g. At higher adsorbent dosages, there were higher unoccupied adsorption sites for removal of Cu2+. As mentioned by Azman et al. (2020), the amount of adsorbed ions is increased as more surface area, active sites and functional groups can be obtained with higher dosages (Azman et al., 2020). As depicted in Figure 4, Cu²⁺ adsorption capacity decreased with higher adsorbent dosage. A similar trend was noticed in a previous study where adsorption



Figure 3. SEM images of prepared polysulphide adsorbent from waste cooking oil and sulphur (a) 100X (b) 500X (c) 1000X (d) 2000X and (e) EDX image.

sites remained unsaturated during the removal because the higher amount of dosages produced more active adsorption sites and introduced steric hindrance for the polysulphide to adsorb the Cu^{2+} ions (Ezeh *et al.*, 2017).

Effect of initial Cu^{2+} *concentration.* The effect of initial Cu^{2+} concentration on the percentage removal is presented in *Figure 5*. The removal percentage dropped from 68.88%-42.87% while the initial Cu^{2+} concentration increased. On the contrary, the Cu^{2+} adsorption capacity increased from 0.03-0.11 mg g⁻¹ when the initial concentration was raised from 1-5 mg L⁻¹. The maximum removal was 68.88% at 1 mg L⁻¹ of Cu^{2+} solution. Because of steric hindrance, the active sites of the polysulphide adsorbent would be surrounded with more Cu^{2+} in the solution when the initial Cu^{2+} concentration was comparatively higher. Therefore, the equilibrium adsorption capacity of polysulphide adsorbent

rises with the increasing Cu^{2+} which enhances the adsorption process (Azman *et al.*, 2020). On the other hand, the removal rate tended to decrease at lower initial Cu^{2+} concentration, as the Cu^{2+} ions were removed by the sufficient available active sites of the polysulphide adsorbent (Radnia *et al.*, 2012).

Effect of contact time. The removal efficiency of Cu^{2+} was studied as a function of contact time at the initial concentration of 5 mg L⁻¹ at 35°C and adsorbent dosage of 2 g, which is presented in *Figure 6*. For predicting the equilibrium adsorption, it is crucial to consider the effect of contact time on the adsorption of metal ions on any adsorbent (Emenike *et al.*, 2022). As depicted in the figure, the adsorption of Cu^{2+} into the polysulphide adsorbent increased with the increasing contact time. A similar trend was reported in a previous study (Gorzin & Abadi, 2017). At 0-80 min, the adsorption of Cu^{2+} removal was very fast. The contact time



Figure 4. Effect of adsorbent dosage on the percentage removal and Cu^{2+} adsorption capacity ($C0=5 \text{ mg } L^{-1}$, $T=35^{\circ}C$).



Figure 5. Effect of initial Cu^{2+} concentration on adsorption capacity and percentage removal ($C0=1 \text{ mg } L^{-1}$, $T=35^{\circ}C$ and adsorbent dosage = 2 g).

needed for Cu^{2+} solution to achieve equilibrium was 80 min and saturated between 80-120 min with 77.81% of Cu^{2+} uptake. Initially, the removal rate and Cu^{2+} uptake capacity were rapid. Later, a gradual decline was observed at an equilibrium time beyond which no discernible rise in the removal rate and adsorption capacity was found. The initial rapid adsorption was caused by the abundance and availability of the active sites on polysulphide adsorbents. The active sites were rapidly occupied by Cu^{2+} ions and then became saturated upon reaching equilibrium (Ezeh *et al.*, 2017; Gorzin & Abadi, 2017). Adsorption isotherm. Adsorption isotherm is important to understand the removal process. In this study, Cu^{2+} removal was analysed by both Langmuir and Freundlich isotherm. But the process fitted better by Langmuir isotherm. The R² value of Langmuir value was higher than the Freundlich model. The Cu^{2+} -polysulphide interaction is the main reason behind this (Ko *et al.*, 2021). *Figure 7* represents the isothermal curves for both Langmuir and Freundlich isothermal models with a brief exhibition of their parameters in *Table 1*. The R² value is closer to 1 for Langmuir model, which means it is more favourable and efficient.



Figure 6. Effect of contact time on adsorption capacity and percentage removal ($C0=5 \text{ mg } L^{-1}$, $T=35^{\circ}C$ and adsorbent dosage = 2 g).



Figure 7. Adsorption isotherm graph of Cu^{2+} removal (a) Freundlich, and (b) Langmuir model.

TABLE 1. PARAMETERS OF ISOTHERMAL STUDY OF Cu²⁺ REMOVAL

Langmuir			Freundlich			
Q _{max}	K _L	R _L	\mathbb{R}^2	K _f	1/n	R ²
0.1480	0.9755	2.9755	0.99977	15.1600	1.90146	0.9773

The highest removal recorded in this study is 77.81%. It was achieved using a relatively higher polysulphide adsorbent dosage (5 g in 5 mg L⁻¹ Cu²⁺ solution) which is higher than other heavy metals using the same adsorbent (Naveem et al., 2023). There are several factors behind this removal percentage for Cu2+ in this study. The surface area, pore volume and pore diameter were 19.59 m³ g⁻¹, 0.018 cm³ g⁻¹ and 36.83 Å, respectively. Although the surface of the polysulphide was modified using NaCl, the attributes of the surface of the adsorbent were not high. The investigations showed that NaCl provides lesser surface area compared to other modifications processes such as electrospinning, carbonisation and supercritical carbon foaming (Nayeem et al., 2023). Moreover, the assumed hydrophobic nature and absence of hydrogen bonds of the vegetable oil based polysulphide adsorbent played a role for relatively low removal percentage (Hasell et al., 2016; Lin et al., 2019; Mann et al., 2021).

CONCLUSION

In this study, polysulphides were prepared from sulphur and waste cooking oil in the ratio of 9:1 by inverse vulcanisation. The study was carried out to investigate the ability of polysulphide adsorbent in the removal of Cu²⁺ ions. It was found that the adsorption is highly influenced by the following parameters such as initial Cu²⁺ concentrations, adsorbent dosage, and contact time. The percentage removal of Cu²⁺ was increased, with the increase of adsorbent dosage. On the other hand, the Cu²⁺ removal efficiency was decreased when the initial Cu²⁺ concentration was increased. The highest percentage removal of copper was recorded at 77.81% with 5 g of adsorbent in 5 mg L^{-1} in aqueous solution. It was found that the equilibrium time for Cu²⁺ adsorption onto polysulphide adsorbent was 80 min. The data obtained best fitted the Langmuir isotherm model with R^2 = 0.9997. The results retrieved from this study have proven the ability of polysulphide adsorbent as a low-cost adsorbent. With proper research and development that can be carried out in the future, it shall be useful to be used in an up-scale treatment of contamination of other heavy metals, not only copper.

ACKNOWLEDGEMENT

The study was supported through RDU 1901185 (Ref. FRGS/1/2019/TK02/UMP/02/22).

REFERENCES

- Azman, N. A. A., Mohd-Azoddein, A., & Ali, M. F. (2020). Polymer sorbent for mercury removal from aqueous solution. *IOP Conference Series: Materials Science and Engineering*, 736(5), 052020. https://doi.org/10.1088/1757– 899X/736/5/052020
- Abraham, A. M., Kumar, S. V., & Alhassan, S. M. (2017). Porous sulphur copolymer for gasphase mercury removal and thermal insulation. *Chemical Engineering Journal*, 332, 1–7. https:// doi.org/10.1016/j.cej.2017.09.069
- Arbabi, M., & Golshani, N. (2016). Removal of copper ions Cu (II) from industrial wastewater: A review of removal methods. *International Journal* of Epidemiological Research, 3(3), 283–293.
- Braga, E. S., & Ricardo, R. D. (2021). Background concentration of copper and cadmium in water from a high industrialized and urban coastal system (Baixada Santista, Brazil) - Contribution to a monitoring program. *Journal of Geosciences* and Environmental Protection, 9(1), 132–150. https://doi.org/10.4236/gep.2021.91011
- Chalker, J. M., Worthington, M. J. H., Lundquist, N. A., & Esdaile, L. J. (2019). Synthesis and applications of polymers made by inverse vulcanization. *Topics in Current Chemistry*, 377(3). https://doi.org/10.1007/s41061-019-0242-7
- Chalker, J. M., Mann, M., Worthington, M. J. H., & Esdaile, L. J. (2021). Polymers made by inverse vulcanization for use as mercury sorbents. *Organic Materials*, 03(02), 362–373. https://doi.org/10.1055/a-1502-2611
- Cheraghipour, E., & Pakshir, M. (2020). Environmentally friendly magnetic chitosan nano-biocomposite for Cu(II) ions adsorption and magnetic nano-fluid hyperthermia: CCD-RSM design. *Journal of Environmental Chemical Engineering*, 9(2), 104883. https://doi. org/10.1016/j.jece.2020.104883
- Chung, W. J., Griebel, J. J., Kim, E. T., Yoon, H., Simmonds, A. G., Ji, H. J., Dirlam, P. T., Glass, R. S., Wie, J. J., Nguyen, N. A., Guralnick, B. W., Park, J., Somogyi, A., Theato, P., Mackay, M. E., Sung, Y., Char, K., & Pyun, J. (2013). The use of

elemental sulfur as an alternative feedstock for polymeric materials. *Nature Chemistry*, 5(6), 518– 524. https://doi.org/10.1038/nchem.1624

- Ciobanu, A. A., Bulgariu, D., Ionescu, I. A., Puiu, D. M., Vasile, G. G., & Bulgariu, L. (2023). Evaluation of thermodynamic parameters for Cu(II) ions biosorption on algae biomass and derived biochars. *Symmetry*, *15*(8), 1500. https://doi. org/10.3390/sym15081500
- Darweesh, M. A., Elgendy, M. Y., Ayad, M. I., Ahmed, A. M., Elsayed, N., & Hammad, W. (2022). Adsorption isotherm, kinetic, and optimization studies for copper (II) removal from aqueous solutions by banana leaves and derived activated carbon. *South African Journal of Chemical Engineering*, 40, 10–20. https://doi.org/10.1016/j. sajce.2022.01.002
- Emenike, E. C., Adeniyi, A. G., Omuku, P. E., Okwu, K. C., & Iwuozor, K. O. (2022). Recent advances in nano-adsorbents for the sequestration of copper from water. *Journal of Water Process Engineering*, 47, 102715. https://doi.org/10.1016/j. jwpe.2022.102715
- Ezeh, K. A., Ogbu, I. C., Akpomie, K. G., Ojukwu, N. C., & Ibe, J. C. (2017). Utilizing the sorption capacity of local Nigerian sawdust for attenuation of heavy metals from solution: Isotherm, kinetic, and thermodynamic investigations. *The Pacific Journal of Science and Technology*, 18(1), 251–264.
- Gomez, I., Mecerreyes, D., Blazquez, J. A., Leonet, O., Youcef, H. B., Li, C., Gómez-Cámer, J. L., Bondarchuk, O., & Rodriguez-Martinez, L. (2016). Inverse vulcanization of sulfur with divinylbenzene: Stable and easy processable cathode material for lithium-sulfur batteries. *Journal of Power Sources*, 329, 72–78. https://doi. org/10.1016/j.jpowsour.2016.08.046
- Gonçalves, F. J., Gurgel, L. V. A., Soares, L. C., Teodoro, F. S., Ferreira, G. M. D., Coelho, Y. L., Da Silva, L. H. M., Prim, D., & Gil, L. F. (2021). Application of pyridine-modified chitosan derivative for simultaneous adsorption of Cu(II) and oxyanions of Cr(VI) from aqueous solution. *Journal of Environmental Management*, 282, 111939. https://doi.org/10.1016/j.jenvman.2021.111939
- Gorzin, F., & Abadi, M. B. R. (2017). Adsorption of Cr(VI) from aqueous solution by adsorbent prepared from paper mill sludge: Kinetics and thermodynamics studies. *Adsorption Science* & *Technology*, 36(1-2), 149–169. https://doi. org/10.1177/0263617416686976

- Hasell, T., Parker, D. J., Jones, H. A., McAllister, T., & Howdle, S. M. (2016). Porous inverse vulcanised polymers for mercury capture. *Chemical Communications*, 52(31), 5383–5386. https://doi. org/10.1039/C6CC00938G
- Jones, E. R., Van Vliet, M. T. H., Qadir, M., & Bierkens, M. F. P. (2021). Country-level and gridded estimates of wastewater production, collection, treatment and reuse. *Earth System Science Data*, 13(2), 237–254. https://doi.org/10.5194/essd-13-237-2021
- Ko, L., Huang, Y., & Lin, Y. A. (2021). Bipyridinecontaining polysulfide materials for broadspectrum removal of heavy metals from water. *ACS Applied Polymer Materials*, 3(7), 3363–3372. https://doi.org/10.1021/acsapm.1c00259
- Kumar, V., Parihar, R. D., Sharma, A., Bakshi, P., Sidhu, G. P. S., Bali, A. S., Karaouzas, I., Bhardwaj, R., Thukral, A. K., Gyasi-Agyei, Y., & Rodrigo-Comino, J. (2019). Global evaluation of heavy metal content in surface water bodies: A metaanalysis using heavy metal pollution indices and multivariate statistical analyses. *Chemosphere*, 236, 124364. https://doi.org/10.1016/j. chemosphere.2019.124364
- Lin, H., Lai, Y., & Liu, Y. (2019). Cross-linkable and Self-foaming polysulfide materials for repairable and mercury capture applications. *ACS Sustainable Chemistry & Engineering*, 7(4), 4515–4522. https:// doi.org/10.1021/acssuschemeng.8b06815
- Mann, M., Luo, X., Tikoalu, A. D., Gibson, C. T., Yin, Y., Al-Attabi, R., Andersson, G. G., Raston, C. L., Henderson, L. C., Pring, A., Hasell, T., & Chalker, J. M. (2021). Carbonisation of a polymer made from sulfur and canola oil. *Chemical Communications*, 57(51), 6296–6299. https://doi. org/10.1039/D1CC01555A
- Nayeem, A., Ali, M. F., & Shariffuddin, J. H. (2022a). Synthesis and applications of inverse vulcanized polysulfides from bio-crosslinkers. *Materials Today Proceedings*, 57, 1095–1100. https://doi. org/10.1016/j.matpr.2021.09.397
- Nayeem, A., Ali, M. F., & Shariffuddin, J. H. (2022b). Polysulfide synthesis using waste cooking palm oil via inverse vulcanization. *Chemical Engineering Technology*, 45(5), 971–978. https:// doi.org/10.1002/ceat.202100465
- Nayeem, A., Ali, M. F., & Shariffuddin, J. H. (2023). The recent development of inverse vulcanized polysulfide as an alternative adsorbent for heavy metal removal in wastewater. *Environmental*

Research, 216, 114306. https://doi.org/10.1016/j. envres.2022.114306

- Radnia, H., Ghoreyshi, A. A., Younesi, H., & Najafpour, G. D. (2012). Adsorption of Fe(II) ions from aqueous phase by chitosan adsorbent: Equilibrium, kinetic, and thermodynamic studies. *Desalination and Water Treatment*, *50*(1-3), 348–359. https://doi.org/10.1080/19443994.2012.720112
- Ramos, S. N. D. C., Xavier, A. L. P., Teodoro, F. S., Gil, L. F., & Gurgel, L. V. A. (2015). Removal of cobalt(II), copper(II), and nickel(II) ions from aqueous solutions using phthalate-functionalized sugarcane bagasse: Mono- and multicomponent adsorption in batch mode. *Industrial Crops and Products*, 79, 116–130. https://doi.org/10.1016/j. indcrop.2015.10.035
- Rashed, M. N., Arifien, A. E., & El-Dowy, F. A. (2023). Preparation and characterization of nanomuscovite by intercalation method for adsorption of heavy metals from polluted water. *Environmental Geochemistry and Health*, 45(7), 5127–5144. https://doi.org/10.1007/s10653-023-01545-4

- Stankovic, S., Sostaric, T., Bugarcic, M., Janicijevic, A., Pantovic-Spajic, K., & Lopicic, Z. (2019). Adsorption of Cu(II) ions from synthetic solution by sunflower seed husks. *Acta Periodica Technologica*, 50, 268–277. https://doi. org/10.2298/apt1950268s
- Tikoalu, A. D., Lundquist, N. A., & Chalker, J. M. (2020). Mercury sorbents made by inverse vulcanization of sustainable triglycerides: The plant oil structure influences the rate of mercury removal from water. *Advanced Sustainable Systems*, 4(3), 1–9. https://doi.org/10.1002/ adsu.201900111
- Worthington, M. J. H., Kucera, R. L., Albuquerque, I. S., Gibson, C. T., Sibley, A., Slattery, A. D., Campbell, J. A., Alboaiji, S. F. K., Muller, K. A., Young, J., Adamson, N., Gascooke, J. R., Jampaiah, D., Sabri, Y. M., Bhargava, S. K., Ippolito, S. J., Lewis, D. A., Quinton, J. S., Ellis, A. V., . . . Chalker, J. M. (2017). Laying waste to mercury: Inexpensive sorbents made from sulfur and recycled cooking oils. *Chemistry - a European Journal*, 23(64), 16219–16230. https:// doi.org/10.1002/chem.201702871